

Avantama AG

Address Laubisruetistrasse 50
8712 Staefa, Switzerland
Email info@avantama.com
Web avantama.com
Phone +41 44 927 13 91



Product Datasheet

Avantama N-11

Ink for Charge Selective Layers in Printed Electronics
Product-No. 7027

Data:

Property	Unit	Result
Appearance	-	translucent, brownish
Solvent	-	mixture of alcohols
Solid content	wt%	2.5
Solid composition	-	crystalline ZnO
Mean primary particle size	nm	12
Mean hydrodynamic particle size	nm	19
Viscosity	cP	2.1
Work function	eV	-3.9
pH (acidity/basicity)	-	pH neutral
Application	-	spin-coating, doctor blading, slot-die

Handling instructions:

- Store in dark at room temperature
- Prior to application: Shake, and optionally filter through 0.2 um or 0.45 um PTFE or PP filter
- Drying of deposited ZnO films at 80°C - 120°C