

Avantama AG

Address Laubisruetistrasse 50
8712 Staefa, Switzerland
Email info@avantama.com
Web avantama.com
Phone +41 44 927 13 91



Product Datasheet

Avantama N-13

Ink for Charge Selective Layers in Printed Electronics
Product-No. 9010

Data:

Property	Unit	Result
Appearance	-	translucent, brownish
Solvent	-	ethanol
Solid content	wt%	20
Solid composition	-	crystalline ZnO
Mean primary particle size	nm	12
Mean hydrodynamic particle size	nm	12
Viscosity	cP	1.8
Work function	eV	-4.3
pH (acidity/basicity)	-	pH neutral
Application	-	Lab and industrial printing processes

Handling instructions:

- Store in dark at room temperature
- Dilute to required concentration
- Prior to application: Shake, and optionally filter through 0.2 um or 0.45 um PTFE or PP filter
- Drying of deposited ZnO films at 80°C - 120°C